



KANOUPRECISION (HONG KONG)CO.,LTD

Add :4 Floor, No.70 XinTian Avenue,Fuyong Town,Baoan District,Shenzhen,china

Email:sales01@gelivableglass.com Tel:+86-18218805996 Fax:+86-755-29786862

Capability Table Of Custom Cover Glass				
Dimension	5"	7"	10"	15"
Tolerance of Shape	±0.05mm	±0.05mm	±0.05mm	±0.05mm
Tolerance of Print	±0.1mm	±0.1mm	±0.1mm	±0.1mm
Hole	Min.:φ1.0mm			
Chemical strengthening	Gorilla Glass 3: CS>650Mpa,DOL>40um Gorilla Glass 4: CS>850Mpa,DOL>60um Asahi Glass: CS>450Mpa,DOL>8~12um			
Hardness	Gorilla Glass: 9H Asahi Glass: 7H			
Radius Corner	Min.:R0.3±0.05			
Chamfer Corner	Min.:C0.3±0.05			
Radius edge	Min.:C0.15±0.05			
Chamfer edge	Min.:R0.15±0.05			
Width of print	Min. ≥0.2mm			
Thickness of print	6~8um/layer			
AF Coating	Water contact angle:110±5°			
Transmittance Of AR Coating	Single side AR >94%, Double side AR>98%			
Gloss Of Etching AG glass	35/50/70/95/110 (±10)			
Capacity	5.5 clear glass":2500K pcs/M 5.5"glass with 5 times of print :1200K pcs/M			